# PENECOAT<sup>TM</sup> CLEAR TILE PRIMER Version, Penetron Romania Rev.2

# POLYURETHANE PRIMER FOR NON POROUS SUBSTRATES

# DESCRIPTION

PENECOAT<sup>™</sup> CLEAR TILE PRIMER is a transparent, single component adhesion promoter, that chemically activates ceramic and glass surfaces, providing excellent adhesion to the coating that follows. Solvent based. Cures by reaction with ground and air moisture.

# **RECOMMENDED FOR**

PENECOAT™ CLEAR TILE PRIMER is mainly used as an adhesion promoter (primer) for PENECOAT™ CLEAR transparent polyurethane coating, on non-absorbent glazed surfaces, like:

- Glazed ceramic tiles
- Glass
- Glass-brick walls, etc

# ADVANTAGES

- Easy application (ready-to-use)
- Excellent anchoring to non-porous substrates
- UV stable

- Fast curing
- Degreases effectively the surface
- Low cost

# DIRECTIONS FOR USE

**Surface Preparation:** The surface needs to be clean, dry and sound, free of any contamination, which may harmfully affect the adhesion of the coating. Remove all loosing materials. New concrete structures need to dry for at least 28 days. Maximum moisture content should not exceed 5%. Old coatings, dirt, fats, oils, organic substances and dust need to be removed by a grinding machine. Any loose surface pieces and grinding dust need to be thoroughly removed.

NOTE: Careful surface preparation is essential for optimum finish and durability. Do not wash surface with water.

Mixing: Stir PENECOAT™ CLEAR TILE PRIMER, thoroughly, using a mixing drill, prior to application.

**Application:** Prime (activate) non-absorbent glazed surfaces, with PENECOAT<sup>™</sup> CLEAR TILE PRIMER. Apply PENECOAT<sup>™</sup> CLEAR TILE PRIMER, by soaking a clean and dry cloth, and wipe the entire surface off. By this application procedure, you ensure, that, besides the chemical activation (priming) of the surface, the surface is getting also very effectively degreased. Change cloths often. Make sure that enough quantity of PENECOAT<sup>™</sup> CLEAR TILE PRIMER is applied on the entire surface to be primed and make sure that you do not leave any untreated spots.

After approx. 1-2 hours, apply PENECOAT™ CLEAR, PENECOAT™ ELASTIC or other similar coatings.

**NOTE:** Apply PENECOAT<sup>™</sup> CLEAR MAT FINISH, 12 hours after the last layer of PENECOAT<sup>™</sup> CLEAR.

#### COVERAGE

50 - 80 g/m<sup>2</sup> (0,01 – 0,02 lb/ft<sup>2</sup>) applied in one or two layers.

This coverage is based on application by soaked cloth onto a smooth surface in optimum conditions. Factors, like surface porosity, temperature and application method, can alter consumption.



# SPECIAL CONSIDERATIONS

For the best results, the temperature application and curing should be between 5 °C to 35 °C (41 °F to 95 °F). Low temperatures cause curing retardation, while high temperatures speed up curing. High humidity may affect the final finish.

#### POLYURETHANE PRIMER FOR NON POROUS SUBSTRATES

PENECOAT<sup>™</sup> CLEAR TILE PRIMER and PENECOAT<sup>™</sup> CLEAR or PENECOAT<sup>™</sup> ELASTIC must be applied on the same day, so as to achieve optimum bonding between layers.

A test application is highly recommended prior to application of PENECOAT<sup>™</sup> CLEAR TILE PRIMER/PENECOAT<sup>™</sup> CLEAR, on surfaces coated with silanes, siloxanes, silicones, or other hydrophobic materials, if quality and surface conditions are not well specified, due to expected low adhesion.

Hands and tools should be cleaned before polymerization, with the solvent PENECLEANER™ A PLUS.

Contact PENETRON ROMANIA for further information, regarding your project.

#### PACKAGING

PENECOAT  $^{\text{TM}}$  CLEAR TILE PRIMER is available in 4 kg (9 lb) and 1 kg (2,2 lb) containers.

#### **STORAGE / SHELF LIFE**

PENECOAT<sup>™</sup> CLEAR TILE PRIMER can be stored for 9 months in its original packing (unopened container) at 5 °C - 35 °C (41 °F - 95 °F) in a cool, dry place. Keep away from wet areas and direct sunlight.

#### SAFE HANDLING INFORMATION

Flammable. No smoking. Avoid skin and eye contact. If contact is made, flush areas with lots of water and seek medical advice. Protective gloves, mask and goggles should be worn. For further information please refer to Safety Data Sheet. Each Safety Data Sheet contains health and safety information for the protection of your employees and your customers. KEEP OUT OF REACH OF CHILDREN.

#### WARRANTY - DISCLAIMER

BEST IMPORT PRODUCTS PENETRON. warrants that the products manufactured by it shall be free from material defects and will conform to formulation standards and contain all components in their proper proportion. Should any of the products be proven defective, the liability to BEST IMPORT PRODUCTS PENETRON shall be limited to replacement of the material proven to be defective, and BEST IMPORT PRODUCTSPENETRON shall in no case be liable otherwise or for incidental or IMPORT consequential damage.BEST PRODUCTS NOWARRANTY PENETRON MAKES AS TO MERCHANTABILITY OR FITNESS FORA PARTICULAR PURPOSE AND THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED. User shall determine the suitability of the product for its intended use and assume all risks and liability in connection there with. BEST IMPORT PRODUCTS PENETRON particularly mav differentiate its versions of the product's data sheet compared with those of PENETRON INTERNATIONAL LTD data sheet or respective PENETRON companies worldwide. These changes are due to text formatting, different application weathering and procedures or different product names and aim at the optimal consumer information

#### CERTIFICATION

# CE

PENETRON HELLAS S.A. 50 Thrakomakedonon Av., 136 79 Acharnes, Greece 22 1128-CPR-10.09.0479 DOP NO: 14.013-01-01D160922-05 EN 1504-2 PENECOAT CLEAR TILE PRIMER Surface protection product - coating: Protection against ingress [Method 1.3] (Used with PENECOAT CLEAR and PENECOAT CLEAR MAT FINISH) Linear shrinkage: NPD Coefficient of thermal expansion: NPD Adhesion by cross-cut test: NPD Permeability to CO<sub>2</sub>: S<sub>D</sub>>50m Water vapour permeability: Class II: 5 m  $\leq$  S<sub>D</sub>  $\leq$  50 m Capillary absorption and permeability to water:  $\omega < 0,1$ kg/m<sup>2</sup>.h<sup>0,5</sup> Thermal compatibility: NPD Resistance to thermal shock: NPD Chemical resistance: NPD Crack bridging ability: NPD Adhesion strength by pull-off test:  $\geq$  1.5 (1.0) N/mm<sup>2</sup> Reaction to fire: Class F Slip / skid resistance: NPD Behavior after artificial weathering: NPD Antistatic behavior: NPD Adhesion on wet concrete: NPD Dangerous substances: According 5.3

> BEST IMPORT PRODUCTS PENETRON Brasov, Str. Fundatura Harmanului, Complex Duplex 2 Departament tehnic Tel: 0742 454 382 / 0368734003 office@penetron.ro www.penetron.ro