

## ALL-PURPOSE TWO-COMPONENT EPOXY RESIN FOR BASE COATS SCRATCH COATS AND AS REPAIR MORTAR

### DESCRIPTION

EP 55 is an all-purpose, high- quality, solvent-free, 2-component epoxy resin. EP 55 is used as a base coat, scratch coat and as levelling mortar. Due to its low-viscosity and good wettability features the resin penetrates into the substrate very well and results in a high-strength base for subsequent coatings. EP 55 is used as a DIBt® (German Institute for Structural Engineering) accredited primer, tested within the system in combination with the water-protecting WHG coatings EP 280 WHG and EP 282 WHG. Its application is especially suitable in installations handling (filling, transferring or storing) materials hazardous to water. EP 55 is tested in combination with the low-emission coating EP 202 and the photo-stable polyurethane coatings PU 410 and PU 420, according to the AgBB procedure.

### RECOMMENDED FOR

Typical areas of application are:

- ◆ Primer and scratch coats
- ◆ Priming filler.
- ◆ Levelling coat and epoxy resin mortar.

### ADVANTAGES

- ◆ High quality epoxy resin
- ◆ No solvents
- ◆ Low Voltage Emission Control System
- ◆ Safe and reliable
- ◆ Good adhesion between layers
- ◆ Multipurpose
- ◆ Resistant to hydrolysis and saponification
- ◆ No harmful substances

### TECHNICAL CHARACTERISTICS

Characteristic	Test Result	Test Method
<i>Viscosit (Components A+B)</i>	850 mPa s	EN ISO 3219 at 73.4 oF (23 oC)
<i>Density (Components A+B)</i>	1.07 kg/lt	EN ISO 2811-2 at 68 oF (20 oC)
<i>Color</i>	Clean - Yellowish	
<i>Solid content</i>	100%	KLB - Method
<i>Weight loss</i>	0.3 % after 28 days	
<i>Water absorption</i>	< 0.2 %	DIN 53495
<i>Bending tensile strength</i>	35 N/mm <sup>2</sup>	DIN EN 196/1
<i>Compressive strength</i>	80 N/mm <sup>2</sup>	DIN EN 196/1
<i>Shore-hardness D</i>	80 after 7 days	DIN 53505
<i>Adhesive tensile strength</i>	> 1.5 N/mm <sup>2</sup>	DIN EN ISO 1542
<i>Processing time at 50 oF (10 oC)</i>	55 minutes	
<i>Processing time at 68 oF (20 oC)</i>	25 minutes	
<i>Processing time at 86 oF (30 oC)</i>	15 minutes	
<i>Processing temperature</i>	50 oF (10 oC) minimum room and floor temperature	
<i>Curing time at 50 oF (10 oC)</i>	12-14 hrs (Accessibility)	
<i>Curing time at 68 oF (20 oC)</i>	6-8 hrs (Accessibility)	
<i>Curing time at 86 oF (30 oC)</i>	5-6 hrs (Accessibility)	

Curing	2-3 days for mechanical load at 68 oF (20 oC) 7 days for chemical resistance at 68 °F (20 oC)	
Further coatings	After curing, but not longer than 48 hours at 68 oF (20 oC)	

*\*The aforementioned results are related to average laboratory test results. In reality the climate changes, such as temperature moisture and surface porosity may change these results.*

#### DIRECTIONS FOR USE

**Surface Preparation:** The substrate to be coated has to be levelled, dry, free of dust, has to have adequate tensile and compressive strength, and be free from weakly-bonded components or surfaces. Materials impairing adhesion, such as grease, oil, and paint residues must be removed using suitable methods. Suitable surfaces are concrete C20/25 (B 25), cement screed CT-C35-F5 (ZE 30), as well as other adequately sound surfaces. The substrate has to have adequately high strength for the proposed occupational use. Coating of mastic asphalt with epoxy resin is not recommended. The surface to be coated should be prepared mechanically, preferably by shot-blasting. The surface strength must then be a minimum of 1.5 N/mm<sup>2</sup>. For concrete, moisture content must not exceed 4.5 CM-%, remaining residual humidity. The possibility of moisture ingress from the rear must be permanently excluded. Please refer to the advice issued by the trade associations, e.g. the current edition of BEB-worksheets KH-0/U and KH- 0/S. Reconstructing floors may need special procedures. Obtain technical advice

**Mixing:** Single packages of the components need to be measured in the precise mixing ratio. Combi-trading units will be supplied in the correctly measured mixing ratio. Component A has sufficient volume for the entire trading unit. Decant the hardener into the resin completely. Blend with a slow speed mixer (200 - 400 r/pm) for at least 2 - 3 minutes, for a material that is homogeneous and free of streaks. To avoid mixing errors it is recommended to empty the resin/hardener-mixture into a clean container and mix briefly once again („to repot“).

#### Producing scratch coats and mortar:

**Scratch coats:** 1.0 kg EP 55 0.5 - 0.8 kg KLB-Mischsand 2/1 (alternatively QUARTZ SAND MIX 0.10 – 0.45 MM)

**Epoxy resin mortar:** 1.0 kg EP 55 8.0 - 12.0 kg KLB-Mischsand 1 Before adding additives, premix the binding agent. Then add the additive. The amount of the sand blend to be added depends on the desired texture and consistency.

**Mixing ratios:** A:B = 2:1 parts by weight

A:B = 100:55 parts by volume

#### APPLICATION

**Base coat:** Processing the material as a base coat takes place immediately after mixing, using a coating knife, trowel, or nylon roller. Apply an evenly closed coat on the substrate. On highly absorbent surfaces a second coat or a saturated scratch coat is recommended to achieve a compact surface.

For optimum adhesion scatter the fresh surface with approx.0.8 kg/m<sup>2</sup> quartz sand (grain size 0.3/0.8 mm). This is mandatory, if the subsequent coatings will be applied later than 48 hours after base coat application

**Scratch coat:** For smoothing the substrate, as well as pore sealing, apply a scratch coat. Use a trowel, metal- or rubber coating knife. The consistency has to be adjusted according to the absorbency of the substrate, and set so the material may run true.

**Priming filler:** Base coat and the smoothing coat may be applied simultaneously. It just has to be assured that a sufficient sealing coat for subsequent coatings is achieved. Usually prime filling coats may be filled with 0.5 kg of KLBMischsand 2/1 (alternatively QUARTZ SAND MIX 0.10 – 0.45 MM) for 1 kg of binding agent. Apply with a rubber coating knife, with a consumption of 0.7 - 1.0 kg/m<sup>2</sup>, depending on the depth of roughness of the substrate

**Epoxy resin mortar:** Resin: EP 55 is suitable for repair work and leveling. Apply immediately after mix, and spread the material with a smooth spatula. Clean the tools with VR 24.

EP 55 when used as a primer for EP 280 WHG and EP 282 WHG products, please as you will find in the instructions below technical property brochures. Floor and air-temperature must not fall below 50 °F (10 °C) and/or humidity must not exceed 75 %. The difference in floor and room-temperature must be less than 3°. If the application is done at the dew point of the site, traction can be malfunctioning, and ripening and bubbles may appear. The desired curing temperature is at 20 °C. The low temperature may increase the curing time while high temperatures may reduce the curing time.

**NOTE:** The timely instructions are correct and very important to ensure good adhesion between layers.

### COVERAGE

Base coat: Approx. 0.3 – 0.4 kg/m<sup>2</sup>

Scratch coat: Approx. 0.4 – 0.6 kg/m<sup>2</sup>

### SPECIAL CONSIDERATIONS

We advise against the „gumming“ of screed joints/flat joints with pure or with thixotropic agent filled epoxy resin. In the course of time, these areas will begin to show on the surface.

For the application, use always the KLB-Primer resin in combination with quartz sand e.g. KLB-Mischsand 2/1 (alternatively QUARTZ SAND MIX 0.10 – 0.45 MM) or KLB-Mischsand 1. For this, we recommend to add at least 1 – 3 parts by weight of filler. To remove fresh contamination and to clean tools, use thinners VR 24 or VR 33 immediately. Hardened material can only be removed mechanically. The product is subject to the hazardous material-, operational safety-, and transport-regulations for hazardous goods. Refer to the DIN-Safety Data Sheet and the information on the labelled containers!

GISCODE: (05/2018 modification) RE 30 Indication of VOC-Content: (EG-Regulation 2004/42).

Maximum Permissible Value 500 g/l (2010,II,j/lb): Ready-for-use product contains < 500 g/l VOC.

Contact PENETRON ROMANIA. for additional information, regarding your project.

### PACKAGING

The EP 55 is available in 6.6 + 3.4 kg and 20 + 10 kg containers

### STORAGE / SHELF LIFE

Store in dry and frost-free conditions. Ideal storage temperature is between 50 - 68 °F (10 - 20 °C). Bring to a suitable working temperature before application. Tightly reseal opened containers and use the content as soon as possible. When properly stored in a dry place in unopened and undamaged original packaging, shelf life is 12 months.

### SAFE HANDLING INFORMATION

Avoid skin and eye contact. If contact is made, flush areas with lots of water and seek medical advice. Protective gloves, mask and goggles should be worn. For further information please refer to PENETRON ROMANIA

**KEEP OUT OF REACH OF CHILDREN.**

### CERTIFICATION

AgBB-tested and DIBt®-accredited in combination with various coatings.

Checked as primers for coating systems water protection WHG.

Ask for the laboratory structure KLB

**WARRANTY – DICLAIMER**

**BEST IMPORT PRODUCTS PENETRON.** warrants that the products manufactured by it shall be free from material defects and will conform to formulation standards and contain all components in their proper proportion. Should any of the products be proven defective, the liability to BEST IMPORT PRODUCTS PENETRON. shall be limited to replacement of the material proven to be defective, and BEST IMPORT PRODUCTS PENETRON shall in no case be liable otherwise or for incidental or consequential damage.

**BEST IMPORT PRODUCTS PENETRON MAKES NO WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AND THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED.** User shall determine the suitability of the product for its intended use and assume all risks and liability in connection therewith.

BEST IMPORT PRODUCTS PENETRON may particularly differentiate its versions of the product's data sheet compared with those of PENETRON INTERNATIONAL LTD or respective PENETRON companies worldwide. These changes are due to text formatting, different application weathering and procedures or different product names and aim at the optimal consumer information.



KLB Kötztal Lacke + Beschichtungen  
GmbH  
Günztalstraße 25  
FRG-89335 Ichenhausen  
13  
EP30-V1-022013  
DIN EN 13813:2003-01  
Synthetic resin screed mortar  
DIN EN 13813: SR-B1.5-AR0.5-IR5  
Fire behavior: Efl-s1  
Emission of corrosive substances: SR  
Wear resistance BCA: AR 0.5  
Adhesive tensile strength B 1.5  
Impact resistance: IR 5

BEST IMPORT PRODUCTS PENETRON  
Departament Tehnic  
Tel: 0368 734 003  
tehnic@penetron.ro  
Adresa : Complex Duplex 2  
Str. Fundatura Harmanului,  
Brasov  
[www.penetron.ro](http://www.penetron.ro)