

FLEXIBLE POLYURETHANE INJECTION RAPID WATER STOPPING MATERIAL

DESCRIPTION

PENETRON INJECTION FOAM (F) is a rapid foaming, solvent free, water reactive polyurethane injection foam system. When reacted with a catalyst it forms a dense, flexible, fine cellular foam to temporarily stop water leakage.

RECOMMENDED FOR

PENETRON INJECTION FOAM (F) is recommended to stop water penetration from cracks, voids and joints in concrete structures, brickwork, and natural and artificial stonework. To achieve permanent sealing PENETRON INJECTION RESIN should be injected subsequently. Typical areas of application are:

- Tunnels
- Basements
- Diaphragm walls
- Manholes
- Reservoirs
- Water tanks
- Pools
- Soil Stabilization

ADVANTAGES

- Long pot life when mixed component is kept in closed condition.
- Unconfined expansion volume is more than 15 times.
- Reacts only in contact with water and humidity.
- Excellent bonding to wet surfaces.

TECHNICAL CHARACTERISTICS

Typical properties at 70°F (21°C)

	Part A - Base	Part B - Catalyst
Color	Brown	Colorless, water white
Form	Liquid	Liquid
Density	1.16 kg/l	1.07 kg/Lt
Viscosity	100 – 400 cP	25 - 100 cP

Properties @ standard mix ratio of A : B = 20 : 1.5 by weight of resin to catalyst [12.3 : 1 by volume at 68°F (20°C)]:

Foam start time	5 seconds
Foam end time	20 seconds
Max volume expansion	15 - 20 times (unconfined)
Pot life (when not in contact with water)	5 – 9 hours in closed condition
Application temperature	41 to 104°F (5 to 40°C)

All data are average values obtained under laboratory conditions. Impractical use, temperature, humidity and absorption of the substrate may influence the above given values.

DIRECTIONS FOR USE

Application tools: Use single compartment injection pump.

Wet conditions: Add catalyst to PENETRON INJECTION FOAM (F) as per standard given ratio. Mix quickly and thoroughly. Use only required quantity of this mixture for injection through single component pump.

Dry conditions: After installing packers flush the cracks with water thoroughly to wet the injection area. Add catalyst to PENETRON INJECTION FOAM (F) as per standard given ratio. Mix quickly and thoroughly. Use only required quantity of this mixture for injection through single component pump.

FLEXIBLE POLYURETHANE INJECTION RAPID WATER STOPPING MATERIAL

Note: Foam reaction and expansion volume depends upon velocity of water, surrounding temperature, material temperature, pressure and flow rate. For permanent sealing, use PENETRON INJECTION RESIN.

SPECIAL CONSIDERATIONS

Once injection work is completed, immediately flush the pump and hose line with PENETRON PUMP FLUSH.

Contact PENETRON ROMANIA. for additional information, regarding your project.

PACKAGING

Part A Base: 5 gallons (19 Lt) pails

Part B Catalyst: 1.63 quart (1.54 Lt) jugs

STORAGE / SHELF LIFE

PENETRON INJECTION FOAM (F) must be stored in a dry enclosed area off the ground at a minimum temperature of 45°F (7°C). Shelf life when stored in proper conditions in unopened, undamaged packaging is 12 months.

SAFE HANDLING INFORMATION

KEEP OUT OF REACH OF CHILDREN. For further information please refer to PENETRON ROMANIA.

WARRANTY - DISCLAIMER

BEST IMPORT PRODUCTS PENETRON. warrants that the products manufactured by it shall be free from material defects and will conform to formulation standards and contain all components in their proper proportion. Should any of the products be proven defective, the liability to BEST IMPORT PRODUCTS PENETRON. shall be limited to replacement of the material proven to be defective, and BEST IMPORT PRODUCTS PENETRON shall in no case be liable otherwise or for incidental or consequential damage.

BEST IMPORT PRODUCTS PENETRON MAKES NO WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AND THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED. User shall determine the suitability of the product for its intended use and assume all risks and liability in connection therewith. BEST IMPORT PRODUCTS PENETRON may particularly differentiate its versions of the product's data sheet compared with those of PENETRON INTERNATIONAL LTD or respective PENETRON companies worldwide. These changes are due to text formatting, different application weathering and procedures or different product names and aim at the optimal consumer information